



MARTINAL[®] OL-104 ZO / OL-107 ZO

Einsatzbeispiele / Applications

Mit einem Vinylsilan beschichtetes, feinteilig gefälltes Aluminiumhydroxid zur Verbesserung der mechanischen, rheologischen und elektrischen Eigenschaften für vernetzbare Polyolefine und Kautschukmischungen.

Vinyl silane treated, finely precipitated aluminum hydroxide to improve mechanical, rheological and electrical properties in curable polyolefinic and rubber compounds.

Durchschnittsanalyse / Typical analysis

		OL-104 ZO	OL-107 ZO
Al(OH) ₃ -Gehalt /-content	[%]	≈ 99.0	≈ 99.0
Feuchte / Moisture (105 °C)	[%]	≤ 0.35	≤ 0.4
Glühverlust / Loss on Ignition (1200 °C)	[%]	≈ 35	≈ 35
Na ₂ O löslich / soluble	[%]	≤ 0.08	≤ 0.08
Brechungsindex / Refractive index	[%]	1.58	1.58
Teilchengröße (Laserbeugung, Cilas) / Particle Size (Laser scattering, Cilas)			
	d50 [µm]	1.7 – 2.1	1.6 – 1.9
Spezifische Oberfläche / Specific Surface Area (BET)	[m ² /g]	3 – 5	6 – 8
Dichte / Density	[g/cm ³]	2.4	2.4
Schüttdichte / Bulk Density	[kg/m ³]	≈ 500	≈ 450
Wärmebeständigkeit / Thermal Stability (Temp. at 2% weight loss, 1 K/min)	[°C]	≈ 225	≈ 220

Anmerkung: Spezifische Oberfläche und Teilchengröße wurden am unbeschichteten Material gemessen.
Remark: Specific surface area and particle size relate to measurements of the uncoated material.

Die oben genannten Werte sind nur als Richtwerte zu verstehen und nicht etwa als zugesicherte Eigenschaften.
The above mentioned values should be taken only as indications and not as guaranteed properties.

Shipping Information

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

Chem. Bezeichnung / Chem. name: Aluminum Hydroxide
Formel / formula: Al(OH)_3
CAS No.: 21645-51-2
EC/EINECS No.: 244-492-7

EUROPE, MIDDLE EAST, AFRICA

Martinswerk GmbH
Kölner Straße 110
D-50127 Bergheim

Phone: +49-2271-902-0
Fax: +49-2271-902-710

Web: www.martinswerk.de
www.hubermaterials.com

AMERICAS

Huber Engineered Materials
3100 Cumberland Boulevard
Suite 600
Atlanta, Georgia 30339

Phone: +1 (678) 247-7300
Fax: +1 (678) 247-2797

Email: info@martinswerk.com
hubermaterials@huber.com

ASIA PACIFIC

Huber Fire Retardant Additives
(Qingdao) Co.Ltd
8th Floor No.2 Building, No.7,
Wuyishan Road, Huangdao District,
Qingdao – China

Phone: +86 532-58792008
Fax: +86 532-58792008



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Martinswerk's Standard Conditions of Sale for the only express warranties applicable to the Martinswerk products. Products incorporating Martinswerk products are not warranted by Martinswerk. In no event is Martinswerk liable for consequential damages. **MARTINAL**® is used, applied for, or registered as a trademark of Martinswerk GmbH in various countries around the world.
© July 2017 Martinswerk GmbH